

# ORAPAPER

## 2040

### Description

White matt satinized wood- free writing paper.

### Release paper

Wood- free, clay coated heavy weight paper, silicone coated on one side, 90 g/m<sup>2</sup>.

### Adhesive

Polyacrylic, permanent adhesive.

### Areas of use

Versatile use, suitable for all common printing methods.

### Technical data\*

---

#### Self- adhesive paper

---

<b>Thickness</b>	83 microns
<b>Weight</b>	80 g/m <sup>2</sup>
<b>Elongation at break</b> (DIN 53 112)	along min. 83 N/ 15 mm across min. 45 N/ 15 mm
<b>Opacity</b> (DIN 53 146)	83 %
<b>Adhesive power</b> (FINAT FTM-2, after 20 min., stainless steel)	min. 9 N/ 25 mm
<b>Initial adhesion</b> (FINAT FTM-9, stainless steel)	min. 7,5 N/ 25 mm
<b>Siliconized release paper</b>	
<b>Thickness</b>	90 microns
<b>Weight</b>	90 g/m <sup>2</sup>
<b>Minimum application temperature</b>	+5°C
<b>Shelf life</b> (20°C and 50 % relative humidity)	2 years <span style="float: right;">11/00</span>

### Attention:

Surfaces to which the material will be applied must be thoroughly free of dust, grease or other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

\*The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of the material for their specific purpose, prior to use.