

## Description

Cast PVC film with an excellent dimensional stability and optimal processing characteristics. The special adhesive enables adhesion onto lacquered surfaces. Available in white and transparent with a glossy surface. Other colours available upon request.

## Release Paper

Double sided PE-coated paper, silicone coated on one side, 143 g/m<sup>2</sup>

## Adhesive

Solvent polyacrylate, repositionable, permanent, transparent

## Area of Use

Designed specifically for high quality screen printed applications, e.g. letterings, markings and decorations with the highest requirements for solidity and durability.

## Printing Method

Screen printing is recommended. Special inks must be used for UV-offset printing and Flexo-printing.

## Technical Data

<b>Thickness*</b> (without paper and adhesive)	70 micron
<b>Dimensional stability</b> (FINAT TM 14)	Adhered to steel, no shrinkage in cross direction, in length 0,1 mm max.
<b>Temperature resistance**</b>	Adhered to aluminium, -50° C to +110° C, no variation
<b>Sea water resistance</b> (DIN 50021)	Adhered to aluminium, after 100h/23° C no variation
<b>Resistance to solvents and chemicals</b>	At room temperature, 72h after adhesion to aluminium, short-term resistant to most oils and greases, fuels, aliphatic solvents, weak acids and alkalis
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	20 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	Along: > 19 MPa Across: > 19 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	Along: > 120% Across: > 120%
<b>Shelf life***</b>	2 years
<b>Application temperature</b>	> +8° C
<b>Service life by specialist application</b> Under vertical outdoor exposure***	10 years (unprinted)

\* average \*\* in original packaging, at 20° C and 50% relative humidity \*\*\* normal climate of Central Europe

## Note

After printing, the ink must be allowed to thoroughly dry, in order to avoid any issues when later combined with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of the selected lacquers and paints should be tested by the user, prior to the application of the material. Furthermore, the application information published by ORAFOL must be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

### **IMPORTANT NOTICE**

All ORACAL® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORACAL® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORACAL® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

ORACAL® is a registered trademark of ORAFOL Europe GmbH