

BRICK®

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	1000 microns	non adhesive polyester	

APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	60°	150 gf	10 cm/sec	25 seconds	155°C (311°F)	Medium/High (4 bar)	cold

Due to the thickness of the material, we recommend to cut letters with a minimum height of 0,5 cm!

- Mirror cut the design
- Weed excess material
- Preheat the garment for 20 seconds
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier cold

PRODUCT HIGHLIGHTS

- Our thickest product
- Adds dimension to any logo
- Matt finish

NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID 9105027958

