

AURORAPRINT

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	200 microns	non adhesive polyester	  REACH compliant

APPLICATION INSTRUCTIONS | compatible with UV inks



APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends, Spandex	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	60°	80 gf	15 cm/sec	15 seconds	150°C (302°F)	Medium (3,5 bar)	hot

- Print, cut and peel off the excess material
- Remove the print from the carrier with the help of TTD Easy
- Place the decoration on the fabric
- Apply following the recommended parameters
- Remove the TTD while hot

PRODUCT HIGHLIGHTS

- Iridescent appearance and glossy finish
- Colour-shifting properties
- Textured effect
- Suitable for being printed with UV inks

 **NOTE:** Given the large number of inks and printers, we highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	YES best inside-out	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

 This document can be subject to variations. Updated versions are available on www.siser.com
For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID: 9105027958

