DIGIBRICK® UV (EXCLUSIVILY SUITABLE FOR UV PRINTING)

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	650 microns	Non adhesive polyester	VEGANOK AZIENDA N. 1004 · REACH compliant

APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends	60°	80 gf	20 cm/sec	25*seconds	155°C (311°F)	Medium-High (3-4 bar)	hot

→ **Print, cut and peel off excess material**
→ **Remove the print from the carrier and place the decoration on the fabric, covered with parchment paper**
→ **For the best result: Preheat the under-platen at 155°C for 20 sec. before**
→ ***Apply following the recommended parameters**
→ ***When working with TTD / applicationtape: remove the TTD after 5 sec., cover the design with parchment paper and press again for 20 seconds.**

PRODUCT HIGHLIGHTS
→ **High thickness**
→ **3D-effect - ideal for logos and crestes**
→ **Specially designed for UV-prints**

! Due to the thickness of this media, we recommend to raise the head height on your printer (if applicable) to avoid any potential complications. Never use removable media-clamps of your printer for Digibrick!
! We recommend to proceed a print+cut alignment before printing, if applicalbe
! We do not recommend cutting details smaller than 5mm.
! As usual, we recommend doing a test, before using a "new" material

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside- out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

→ **Wait 24 hours after the application before the first wash**
→ **Respect the textile recommendations**
→ **Do not bleach or use aggressive chemical agents**

This document can be subject to variations. Updated versions are available on www.siser.com
For further information, please contact our sales office: info@siser.it

Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246

TÜVRheinland CERTIFIED · Management System ISO 9001:2015 ISO 14001:2015 · www.tuv.com ID 9105027958