SUBLITHIN MATT UV EXCLUSIVELY FOR UP PRINT !

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	110 microns	Non adhesive polyester	VEGANOK AZIENDA N. 1004 · REACH compliant

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
textiles colored with sublimation inks Cotton, Polyster, Poly/Cotton mix	45°	80 gf	20 cm/sec	15 seconds	135°C (275°F)	Medium (2,5-3,0 bar)	hot

→ Print, Cut and peel off excess material
→ Remove the print from the support with the help of TTD Easy
→ Place the decoration on the fabric Apply following the recommended parameters
→ Remove the TTD while hot
→ To get a 3D effect: Fix the transfer with heat application tape on the fabric, put it face down on a teflon cushion on the underplaten and transfer with low pressure.

PRODUCT HIGHLIGHTS
→ Anti migration barrier
→ Suitable for sublimation dyed fabrics, low transfer temperature
→ Specially developed for UV printing

NOTE: Given the large number of sublimation inks and printers, we highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	NO	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

→ Wait 24 hours after the application before the first wash
→ Respect the textile recommendations
→ Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it

Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246

TÜVRheinland CERTIFIED
Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com ID 9105027958