



DATA SHEET 22130.150.39300

SI 130

White polypropylene film, suitable for roll-up-displays, poster, banner, PoS, exhibition displays and illuminated advertising.

Printing Systems







Rolls

Art.Number	Width (mm)	Thickness	Length (m)
22130.150.39300	914	0.150 mm	50
22130.150.30800	1067	0.150 mm	50

Technical data

Characteristic

- High brillance of colours
- Good scratch resistance
- Low-reflective printing surface
- Multi-purpose use, also as synthetic paper and for backlit applications

Finish

• White, semi matt

Specifications

Coating Printside

microporous coating





Width (mm)	914
Thickness	0.150 mm
Core Diameter	76 mm
Length (m)	50
Opacity	0.70
Base Material	Polypropylene
Packing quantity	1 roll

Compatibility

• Suitable for most large format Ink Jet printers using waterbased dye, pigment or latex inks

Handling

- Note for Latex-Inks: To avoid the effect of rewetting (oil film on the print surface due to defective anchorage of ink) it is
 necessary to establish the optimal drying parameter. This can be done by means of print tests before production print.
 Rewetting can appear several days after printing when the drying condtions are defective. The rewetting can also be
 dependent on the given ambient conditions and the composition and consistence of the printing theme. When creating a media
 profile, this circumstance must be expressly taken into consideration.
- If dye inks are used, must be laminated indoor and outdoor to improve light-fastness and smudge-proofness.
- It is necessary to protect the surface if it is subject over a long time to abrasion or any other mechanical influences, to dirt or humidity. The lamination can be done right to the edges or over the edges. The user should check before using what is more appropriate.
- We recommend to use self-adhesive laminating foils for cold lamination.

Storage

After printing the remaining roll must be removed from the plotter and stored in its closed original packing in a cool and dry
environment.

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. These shall be beyond our control, and be subject to your exclusive responsibility. The sale of our products shall be subject to our current General Terms and Conditions.