

STRENGTHENS RESISTANCE FOR GLAZING OVER 3M2 IN AREA

DESCRIPTION

This colourless film forms an integral membrane that holds the glass in place. It prevents the glass from shattering in the event of an explosion or vandalism in places such as shops, shopping centres, schools, hospitals, public buildings, exhibition halls, sports facilities, homes, etc.





SUSTAINABILITY: 5 years for vertical applications in Central Europe.



USE: For all types of glazing.



MAINTENANCE: After 30 days with a standard cleaning solution (non-abrasive, ammonia-free, etc.). Do not use cleaning products that could scratch the surface.



STORAGE: 2 years from delivery. This film should be stored away from excessive humidity and sunlight, at a temperature below 38°C.

In order to meet the highest standards, we recommend that you do not mix films from different productions.

Application notes





Video of the installation





SAFETY FILMS SEC 054X PROTECTIVE FILM

SUPPORT:

ADHESIVE : PROTECTEUR :

THICKNESS: COLOUR:

APPLICATION SIDE : BREAKING LOAD :

ELONGATION AT BREAK:

T° OF APPLICATION :

STANDARDS : FIRE RATING :

CEBTP:

GUARANTEE:

BY ROLL :



PET

Acrylic polymer 25 gr/m2 Siliconised PET 20 microns

110 microns Colorless External

17,5 DA N/CM

100% min, +5°C EUROCLASSES B-s1, d0

NFP 78-406 classification

5 years

1,52 x

10 m 30 m

METHOD OF APPLICATION

The surface to be bonded must be free from dust, grease or any other contaminant. Some materials, such as polycarbonate, can cause bubbling problems. A compatibility test is therefore recommended. Can be installed on plexiglass and polycarbonate.

PRODUCTION AND STANDARDS

In order to constantly improve our products, we may modify colours and manufacturing processes without prior notice. Before applying our films, we recommend that users ensure that they are suitable for the intended use and comply with current standards.

- NOITION -







Showroom: 36 rue Réaumur 75003 Paris

• Head office: P.A. des petits carreaux

2 avenue des Orangers 94380 Bonneuil sur Marne - France

: +33 (0)1 43 99 00 22

: info@reflectiv.com: www.reflectiv.com