

Magnetic Sheeting – Natural

Technical data:

PRODUCT DESCRIPTION: ROLL NATURAL (RAW, BROWN)

THICKNESS: 0.75 & 0.8 MM

COMPOSITION:

- magnetic powder
- chlorinated polyethylene
- soybean oil

PHYSICAL DATA:

BM Art.	Thickness	Dimension (L x B)		Pole pitch	Pull strength	GW
705.021/031	0.75 mm (+/-0.03)	10.000 mm (+300)	615 mm (+2/-0)	2 mm	>38 G/CM2	20 Kg
705.023/031	0.75 mm (+/-0.03)	30.000 mm (+300)	615 mm (+2/-0)	2 mm	>38 G/CM2	56 Kg
705.024/031	0.75 mm (+/-0.03)	15.000 mm (+300)	615 mm (+2/-0)	2 mm	>38 G/CM2	28 Kg
705.025/031	0.75 mm (+/-0.03)	10.000 mm (+300)	1030 mm (+2/-0)	2 mm	>38 G/CM2	31 Kg

705.027/031	0.80 mm (+/-0.03)	10.000 mm (+300)	1000 mm (+2/-0)	2 mm	>42 G/CM2	34 Kg
-------------	----------------------	---------------------	--------------------	------	-----------	-------

PHYSICAL PROPERTIES:

From a temperature of +30°C, the magnetic foil could lose certain % of its adhesive strength.

Magnetic sheet has a UV hardened coating on the magnetic side.

Scissor cutting, knife-cutting, die-cutting and slitting can be done with ease.

- Working Temperature: - 10°C / + 50°C
- Short Term Resistance: 60°C

The material is classified as non-toxic according to EU directives and TSCA (Toxic Substances Control Act), classified as environmentally neutral, REACH and RoHS compliant.

CUSTOM TARIFF NO. (TARIC-Code): 8505 190090